



AS Rubber & Plastics Limited

Elwell Street, West Bromwich B70 0DN

Tel: 0121 520 5782

Website: www.asrubber.com Email: info@asrubber.com

Specification Sheet

AS600 CLOSED CELL POLYETHYLENE FOAM, CFC AND HCFC FREE

<u>Properties</u>	<u>Test Method</u>	<u>Unit</u>	<u>Value</u>
DENSITY	DIN 53420	Kg/m ³	24
TENSILE STRENGTH	DIN 53571	N/mm ²	
Extrusion direction			0,219
Cross direction			0,170
ELONGATION AT BREAK	DIN 53571	%	
Extrusion direction			67
Cross direction			52
COMPRESSION STRENGTH	DIN 53577	N/mm ²	
25% (4 th Compression)			0,024
50% (4 th Compression)			0,081
70% (4 th Compression)			0,200
THERMAL STABILITY (24h at 70°C)	ASTM D-3575-S	%	<0,5
CELL SIZE	BS 4443/1 Met.4	Cells/25mm	>21
WATER ABSORPTION	DIN 53428	Vol %	1,19

(after 24 Hours)

WORKING TEMP RANGE Internal °C -30;+80

April 2024

The information provided in this data sheet is in good faith.

No liability is, however, accepted for errors and omission and in no circumstances shall A S Rubber & Plastics be liable in damages for loss or injury arising directly or as a consequence of the publication of this data sheet.