



AS Rubber & Plastics Limited

Elwell Street, West Bromwich B70 0DN

Tel: 0121 520 5782

Website: www.asrubber.com Email: info@asrubber.com

TECHNICAL DATA SHEET

AS901 Solid Commercial Rubber

Compression Set (22 hours @ 70°C)	ASTM D395	30% Max
Elongation at Break	ASTM D412	250% Min
Max Working Temperature		70°C
Min Working Temperature		-30°C
Shore Hardness (Shore A)	ASTM D2240	70° Shore +/-5°
Specific Gravity	ASTM D2240	1.5g/cm ³ +/- 0.03
Tensile Strength	ASTM D412	3 MPA Min

April 2024