



AS Rubber & Plastics Limited

Elwell Street, West Bromwich B70 0DN

Tel: 0121 520 5782

Website: www.asrubber.com Email: info@asrubber.com

TECHNICAL DATA SHEET

AS902 Solid Neoprene Rubber

Compression Set (22 hours @ 70°C)	ASTM D395	35% Max
Elongation at Break	ASTM D412	250% Min
Max Working Temperature		70°C
Min Working Temperature		-20°C
Shore Hardness (Shore A)	ASTM D2240	65° Shore +/- 5°
Specific Gravity	ASTM D2240	1.5g/cm ³ +/- 0.05
Tensile Strength	ASTM D412	3 MPA Min

April 2024